

Code	Description	Size	Colour
20600	Gorilla MS Sealant	420gm	White
20601	Gorilla MS Sealant	420gm	Grey
20602	Gorilla MS Sealant	415gm	Black
20603	Gorilla MS Sealant	600ml	Black
20604	Gorilla MS Sealant	600ml	Grey
20605	Gorilla MS Sealant	600ml	White
20606	Gorilla MS Sealant	600ml	Concrete Grey
20607	Gorilla MS Sealant	600ml	Taitania

## 1. Description

Gorilla MS Sealant is a single component joint sealant based on MS Polymer Technology.

## 2. Characteristics

- Superior flexibility
- High bond strength on nearly all surfaces
- Excellent adhesion and extrudability, even in adverse conditions
- High performance mechanical properties
- Odourless
- Resists mould growth
- No bubble formation within sealant, even in wet and humid conditions
- Excellent weather resistance in all climates
- Colour stable and excellent UV resistance
- Paintable 1 hour after application under normal conditions with water based paints (Other systems should be tested)
- Low VOC Content
- Free of isocyanates, solvents, halogens and acids

## 3. Technical Data

<b>Base:</b>	MS Polymer
<b>Consistency:</b>	Stable Paste
<b>Curing System:</b>	Moisture Cure
<b>Skin Formation:</b> (20 °C/65% R.H.)	Ca. 10min
<b>Curing Rate:</b> (20 °C/65% R.H.)	2mm/24h
<b>Hardness:</b>	25+/-5 Shore A
<b>Specific Gravity:</b>	1.45g/mL
<b>Temperature Resistance:</b>	-40 °C until +90 °C
<b>Elastic Recovery:</b>	>70%
<b>Movement Capability:</b>	+/- 25%
<b>Elasticity modulus 100%:</b> (DIN 53504)	0.36 n/mm <sup>2</sup>
<b>Tear Strength:</b> (DIN 53504)	1,30N/mm <sup>2</sup>
<b>Elongation at break:</b> (DIN 53504)	>900% (DIN 53504)
<b>VOC (%)</b>	< 2% /
<b>VOC (g/litre)</b>	<30

\* This can vary according to environmental circumstances such as temperature, humidity, substrate, etc.

## 4. Applications

- Movement joints in high rise constructions, sealing between window and door frames.
- Flexible joints in marine and automotive applications.
- Weather-tight expansion joints in “Façade Systems” & many construction types, both residential, commercial, and industrial
- Applications that should be painted with water-based paints.

**5. Packaging**

Cartridge 290ml and Sausage 600ml (net content)

**6. Shelf Life**

15 months in unopened packaging in a dry and cool storage place at temperatures between +5°C and +25°C.

**7. Application Instructions****Surfaces**

Type: All usual porous and non-porous building materials – Stone, metal (see “Limitations” below), PVC, pre-treated wood  
State: Clean, dry, free of dust and grease.  
Preparation: Gorilla MS will stick to damp surfaces – a surface is considered wet when moisture transfer occurs from the substrate. Porous surfaces should be primed with Gorilla® Primer 150 and Gorilla® 696 Surface Activator may be used on non-porous surfaces.

*Due to the range of substrates on the market recommend preliminary compatibility tests prior to commencement of application.*

**Joint Size**

Minimum Width: 5mm  
Maximum Width: 30mm  
Joint Configuration: Depth = 1/2width

**Application**

Method: Caulking Gun  
Backing Material: PE backer rods for correct joint dimension  
Application Temperature: +5°C to +30°C  
Clean: Gorilla Solvent Cleaner immediately after application and before curing  
Repair: With Gorilla MS Sealant  
Finish: With soapy solution

**Chemical Resistance:**

Good resistance to water, aliphatic solvents, mineral oils, grease, diluted inorganic acids and alkalis. Poor resistance to aromatic solvents, concentrated acids and chlorinated hydrocarbons.

**Limitations:**

Gorilla MS Sealant is not suitable against the following materials: PE, PP, PTFE (Teflon), raw Bituminous substrates, copper or copper containing materials (Copper, Brass, Zinc-Bronze)

Gorilla MS Sealant can be used for bonding of natural stone, but it cannot be used as a joint sealant on this type of surface. Gorilla MS Sealant can therefore only be used on the bottom of natural stone tiles. When applying, make sure not to spill any adhesive on the surface of materials.

When using the Gorilla MS Sealant you need to consider environmental considerations when using on substrates such as “ACM” panels – in particular if the material has high thermal movement - as high levels of temperature swing variance (between daytime & night time) at the surface of the panel (+45°C>) can potentially lead to early movement of the sealant in the joint before the surface has fully skinned over. If questions, please discuss with your Soudal Territory representative.

Gorilla MS Sealant may be painted, however due to the large number of paints and varnishes available we strongly suggest a compatibility test before application. The drying time of alkyd resin-based paints may increase.

Gorilla MS Sealant can be applied to a wide variety of substrates. Because specific substrates such as metals, plastics, polycarbonate, etc may differ from manufacturer to manufacturer, we recommend preliminary compatibility tests.

While producing plastics very often releasing agents, processing aids and other protective agents (like protection foil) are used. These should be removed prior to bonding. For optimum adhesion, the use of Gorilla 696 Surface Activator is recommended.

A total absence of UV can cause a colour change of the sealant.

This product cannot be used as a glazing sealant or for the bonding of aquariums.

**Test and Certificates**

Tested and conforms to ISO 116000-F-25LM  
New Zealand: Agriquality Approval (REF #h1540)

New Zealand: BRANZ Appraisal No. 419  
Belgium: ATG 98.2241 (ISO 11600-F-25LM)  
Germany: MPA-NRW 22-0902 5 98 to DIN 18540-F  
UK: BBA SC 007/01 (ISO 11600-F-25LM)

## 8. Maintenance and Inspection of Weather-Tightness Sealant Joints

### Applies to the following joint types:

- Linear joints
- Penetration seals

### Inspection

Soudal recommends that the first inspection of joints is done 6 months following application, followed by an annual inspection. Normally this inspection is combined with the inspection of the painting. The most effective is to judge the joints during a colder season as building materials shrink the most under low temperatures, resulting in the widest joints. This period is best to judge if the sealants are still able to cope with the pressure, and if detachments appear.

### During inspection specifically pay attention to:

Detachments in facades of buildings can result into leakage. When leakage is noticed but the exact cause and location is unclear, the exact spot should be found by testing. We have two methods for this test:

- Test with a (garden) hose. With a hose the facade can be sprayed. While doing this we work downward towards above, while the inside is checked on water entering the building. When no leakage is found this way, the possibility exists the leakage will only appear when rain and wind pressure are combined at the same moment. Wind pressure causes over pressure on the outside while under pressure on the inside appears. This can cause water to be sucked inside through very small openings. With higher building the water can be pushed up and find its way into buildings.
- Test with a smoke pipe. With a smoke pipe, possible leakage can be identified more easily, especially when wind pressure occurs.

**For further details on Maintenance & Inspection of Weather-Tightness Sealant Joints please go to [www.holdfast.co.nz](http://www.holdfast.co.nz)**

## 8. Health and Safety Recommendation

- Apply the usual industrial hygiene.
- For more detailed information, please refer to the SDS.

### Remark

*The directives and data contained in this documentation is provided in good faith and accurately reflect Soudal's knowledge when its products are properly stored, handled and applied under normal conditions in accordance with Soudal's recommendations. In practice, the diversity of the materials, substrates, environments, site conditions, product storage, handling and application are such that no warranty can be given in respect to the merchantability or fit for purpose, of any product. All users must determine the product suitability for their purposes through testing. This technical data sheet and product properties may change without notice so users, suppliers and retailers of Soudal products should always check that the data sheets they have are the latest. To the maximum extent permitted by law, Soudal disclaims all warranties in relation to either the manufacture, storage and end use of the product. All orders are accepted subject to our current terms of trade. **If any clarification is required, please contact Soudal Technical Services or email [info@soudal.co.nz](mailto:info@soudal.co.nz).***

**Last Updated:** 21 April 2021

Supplier contact details:	Soudal Ltd	Freephone: 0800 70 10 80
	14 Avalon Drive	Phone: (07) 847 5540
	Nawton	
	Hamilton 3200	Email: <a href="mailto:sales@soudal.co.nz">sales@soudal.co.nz</a>
	New Zealand	Website: <a href="http://www.soudal.co.nz">www.soudal.co.nz</a>