

Product name:

MultiStop Finishing Compound

Product Line:

Plaster / Render

Product description and its intended use:

It is a plaster for use over general masonry substrates for finishing. This plaster can be blended and sanded to achieve the desired finish. Often 2 coats are applied to achieve a very flat finish.

Patch and repair tilt panels and as a sandable skimcoat to existing plaster surfaces.

MultiStop Finishing Compound is used over all prepared substrates to give an attractive durable surface ready for painting.

Product identifier:

The product name with the production date is printed on the finished bag.

Place of Manufacture:

New Zealand

Legal and Trading Information:

Legal and trading name of the manufacturer(s):	Rockcote Resene Limited
Address of the Manufacturer:	32-50 Vogel Street, Naenae, Lower Hutt
Website Address:	https://reseneconstruction.co.nz
Email Address:	help@reseneconstruction.co.nz
Phone Number:	0800 507040
NZBN:	9429034745786

This product is not subject to a warning or ban under s26 of the Building Act.

Relevant Building Code clauses:

- Clause B1 - Structure - Performance B1.3.1, B1.3.2 and B1.3.4
- Clause B2 - Durability - Performance B2.3.1 (b) 15 years, B2.3.1 (c) 5 years and B2.3.2
- Clause E2 - External Moisture - Performance E2.3.2
- Clause F2 - Hazardous Building Materials - Performance F2.3.1

How the building product is expected to contribute to compliance:

This product is used and has been tested as part of a wider system.

B1 - This product has a low probability of rupturing, becoming unstable, losing equilibrium, or collapsing during construction or alteration and throughout its life. This product has a low probability of causing loss of amenity through undue deformation, vibratory response, degradation, or other physical characteristics throughout its life and during construction or alteration when the building is in use. This product has made allowance for the requirements of this functional requirement.

B2 - When installed in accordance with the system specifications and drawings, it will meet this performance requirement. Based on material properties and history of use, this product has been assessed to have a durability of at least 15 years when installed as part of a system. This product must be installed in accordance with the relevant specifications outlined in the design section of this document.

E2 - When installed in accordance with the system specifications and drawings, it will meet this performance requirement.

F2 - This product is safe when handled in accordance with its Technical and Safety DataSheet. Dust resulting from sanding and mixing compounds may be a respiratory irritant, and the use of suitable respiratory protection is required. This product meets the requirements set out in F2 and will not present a health hazard to people once installed.

Limitations on the use of the building product:

Requires over-coating with a protective coating.

Apply when the temperature is between 5°C and 30°C.

This product should not be applied over wood, PVC or metal-based products.

It should be noted that Resene Construction Systems products do not satisfy code requirements on their own but deliver code-compliant performance when used as part of a Resene Construction System's system and installed in accordance with the specific specifications.

These products must be handled carefully as a finishing material and kept dry during transportation and storage.

Design requirements that would support the use of the building product:

Specific applications, design and installation instructions are available for each system on our website. This outlines where this product should be installed as part of the wider system.

Mix ratio:	15kg plaster requires approx. 4L of water
Coverage:	1mm thick approx. 15m ²
Substrates:	All prepared base coats of plaster
Abrasive strength:	Excellent
Adhesion:	Excellent
Vapour Permeability:	No vapour barrier formed
VOC:	1 grams per litre
Colour:	light grey
Packaging:	15kg bags
Clean up:	Water while the product is wet

Use by:	12 months from date of manufacture
Storage:	Cool, dry place of the ground
Application Temperature:	+ 5 °C to + 30 °C
Usual No Coats:	1 - 2 (dependent on level of finish required)
Drying Time:	24 hours
Touch Dry:	2-4 hours
Dry to Recoat:	12 hours
Film Build:	Approximately 0.5mm dry film build per coat
Thinning:	N/A
Mean Vapour flow rate:	104.31g/m ² d (ASTM E96/E96M-13 Water Method)
Mean Resistance:	1.06MNs/g (ASTM E96/E96M-13 Water Method)
Fire Group Classification:	1-S (Test in accordance with ISO 5660:2002)

Installation requirements:

Building work must be undertaken by competent and experienced tradespersons familiar with installing Resene Construction Systems systems.

Before applying the product, ensure the surface is clean, sound, dry and free from dust, dirt, grease, mould and lichen. Painted surfaces should have a slurry coat applied.

Plaster is applied not greater than 1mm with a steel trowel to a flat finish. A range of finishes can be achieved using sponges or steel trowels. Apply plaster only when the temperature is between 5°C and 30°C and will be in that range for the 24-hour period following application.

MultiStop Finishing Compound should be protected from hot drying winds and direct sunlight for the first 16 hours. Protect newly applied plaster from rain and water runoff for the first 24 hours.

Once the plaster has cured, the MultiStop Finishing compound can be sanded with 120-240 grit sandpaper. Before painting, the surface needs to be thoroughly dusted or wetted to remove residual dusting from the sanding process.

Maintenance, Environmental and Safety Requirements:

Wash equipment and spills as soon as possible with water.

Ensure washing water does not enter waterways. Wet waste should be disposed of in empty bags and, once dry, disposed of in trade waste. The powder is irritating, and appropriate PPE dust masks are advised when handling. The wet compound is alkaline, and prolonged skin contact should be avoided. Wear rubber gloves, dust masks and safety glasses when handling products.

Material Safety Data Sheets are available upon request or access directly from

<https://reseneconstruction.co.nz/technical-library/safety-data-sheets/>